



# PORCELAIN PAVERS

## SRI & SOLAR REFLECTANCE

Paver Color	% Solar Relectance	SRI
Bone	48.4	56
Calstone	48.4	56
Cemento	47.1	54
Cenere	53.2	62
Faro	56.6	67
Geos	51.4	60
Greystone	37.1	41
Alta	36.5	41
Greige	51.9	61
Leatherwood	37.9	41
Sandalo	35.2	38
Sandy White	65.1	79
Silver	44.1	50
Smoke	41.9	48
Tectona	38.6	43
Titan	39.5	44
Kauri	45.9	53
Maple	64.8	78
Nut	35.1	38
Oak	46.9	54
Bluestone	36.4	40
Lapacho	33.1	36
Sirocco	47.7	55
Zinc	44.4	50

SRI testing conducted by Atlas Material Testing Solutions - Nov. 2018

Archatrak Inc.  
2 Wisconsin Circle, Suite 700  
Chevy Chase MD 20815

Tel: 866 206 8316  
sales@archatrak.com  
www.archatrak.com